

# GEOFOAM R-VALUE

## APPLICABLE TO ATLAS GEOFOAM PRODUCTS

Atlas Geofoam is primarily used as a lightweight material to support structural loads in transportation or building applications, but some applications rely on the insulation performance of Atlas Geofoam.

The R-value per inch of Atlas Geofoam has been determined in accordance with ASTM C518, "Standard Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus."

## PHYSICAL PROPERTIES

		EPS12	EPS15	EPS19	EPS22	EPS29	EPS39	EPS46
R-value per inch at 75°F Mean Temperature	°F·ft <sup>2</sup> ·h/Btu (°K·m <sup>2</sup> /W)	3.2 (0.57)	3.9 (0.68)	3.9 (0.69)	4.2 (0.73)	4.4 (0.77)	4.4 (0.77)	4.5 (0.78)
R-value per inch at 40°F Mean Temperature	°F·ft <sup>2</sup> ·h/Btu (°K·m <sup>2</sup> /W)	3.4 (0.60)	4.2 (0.73)	4.3 (0.75)	4.6 (0.80)	4.8 (0.84)	4.8 (0.84)	4.9 (0.86)

VISIT [ATLASMOLDEDPRODUCTS.COM](http://ATLASMOLDEDPRODUCTS.COM) FOR THE LATEST TECHNICAL INFORMATION

**GREATER COVERAGE  
GREATER AVAILABILITY**



Atlas Molded Products, a Division of Atlas Roofing Corporation  
 8700 Turnpike Drive, Suite 400, Westminster, CO 80031  
 Phone: 855.597.4427 | Fax: 303.428.2595 | [AMPinfo@AtlasRoofing.com](mailto:AMPinfo@AtlasRoofing.com)

